

 <b>LAB MEKANIK POLSRI</b>	<b>LEMBAR HASIL PENGUJIAN BAHAN DENGAN METODE HARDNESS BRINNEL</b>	 <b>TEKNIK MESIN</b>
--	--	--

Lembar Data Pengujian

Tanggal Pengujian : 5 April 2016

Nama : Harry Kurniawan (0613 3020 0130)

Muhammad Fadli (0613 3020 0134)

Wanda Talviansyah Putra (0613 3020 0143)

Hasil Pengujian Bahan Poros Dengan Metode Hardness Brinell (HB)

No	Bahan	D (mm)	P (kg)	d (mm)	dr (mm)	HB (kg/mm <sup>2</sup> )
1	Steel	Ø2,5	187,5	d1 = 1,15	1,13	176,970
				d2 = 1,12		
2				d1 = 1,19	1,15	170,609
				d2 = 1,11		
3				d1 = 1,11	1,08	194,199
				d2 = 1,05		
4				d1 = 1,25	1,23	147,463
				d2 = 1,21		
5				d1 = 1,31	1,28	135,330
				d2 = 1,26		

Rumus mencari nilai HB :

$$HB = \frac{2.P}{\pi.D (D - \sqrt{D^2 - dr^2})}$$

Contoh perhitungan HB 1

$$\begin{aligned}
 HB &= \frac{2.P}{\pi.D (D - \sqrt{D^2 - dr^2})} \\
 &= \frac{2.187,5}{3,14.2,5 (2,5 - \sqrt{2,5^2 - 1,13^2})} \\
 &= 176,97 \text{ kg/mm}^2
 \end{aligned}$$

$$\begin{aligned}
 HB \text{ Total} &= \frac{HB1+HB2+HB3+HB4+HB5}{5} \\
 &= 164,914 \text{ kg/mm}^2
 \end{aligned}$$